



MAX<sup>®</sup> manufactures a full line of **Genuine OEM Black Annealed, Electro-Galvanized, Plastic Coated,** and **Stainless Steel Tie Wire** to work effectively and safely in the broadest range of conditions and applications. MAX wire, available in 21-Ga spools 19-Ga spools, and 16-Ga spools, is tested to rigorous quality standards, under tightly controlled manufacturing processes to assure consistent quality and performance. MAX wire is packaged 50 spools to a box, and 40 boxes to a skid. AIRMATIC, one of the largest MAX Rebar Tier distributors in North America, maintains one of the largest inventories of MAX wire, tools, parts, and accessories in the USA.

By purchasing Genuine OEM MAX wire from AIRMATIC, our customers can be assured they are getting quality wire that is manufactured for optimal performance, and designed to work together with MAX Rebar Tiers for the greatest reliability, speed, and tie tightness. Non-OEM, and clone wire does not meet the high quality and performance standards of MAX wire, and will result in higher failure rates which reduce uptime and increase labor and maintenance costs. MAX wire is made of the ideal grades of carbon steel and stainless steel to suit the environment they must endure. The wire is drawn and dead soft annealed to create the greatest possible ductility which provides a tough but pliable wire which is easy to twist but hard to break. MAX carbon steel wire is sold in 21-Ga (898-series),19-Ga (1061T-series) or 16-Ga (1525-series) thickness (size based on tool model needed), with each size available in three finishes:

TW898: 21-Ga wire; 3 wraps/tie; 312-ft/spool; 120-210 ties/spool (based on rebar size); 50 spools/box.\*
TW1525: 16-Ga wire; 1 wrap/tie; 82-ft/spool; 120-130 ties/spool (based on rebar size); 50 spools/box.\*
TW1061T: 19-Ga wire; 1-Twin wrap/tie; 215-ft/spool; 240 ties/spool (based on rebar size); 30 spools/box.\*
\*Specs f/ Black Annealed; Electro-Galvanized; Plastic Coated.

#### **BLACK ANNEALED**

This low carbon steel, dead soft annealed wire is coated with a black oxide finish to provide a thin, mildly corrosion-resistant finish. This commonly used wire meets most construction, precast, and pre-stressed concrete industry applications.

#### **ELECTRO-GALVANIZED**

This low carbon steel, dead soft annealed wire is finished with a 5-micron zinc coating to provide greater corrosion resistance. It is ideal for precast or pre-stressed concrete used in marine or other harsh environment applications, or where length of service is important.

### PLASTIC COATED

This low carbon steel, dead soft annealed wire is powder-coated with .05mm thickness of yellow polymer (polyester). It is used when tying epoxy coated rebar or other DOT mandated uses, or anywhere a cushioned wire with added protection against corrosion or abrasives is needed.



TW898 TW898-USA



**TW898-EG** 

TW1525

**TW1525-EG** 



TW1061T TW1061T-USA



TW1061T-EG



TW898-PC

TW1525-PC TW1061T-PC





*USA Made*, *BUY AMERICA Certified Wire*, and can be used in the RB218, RB398, RB441T, RB611T, and the RB518 rebar tiers.







# & SAFETY DATA

# **TW1061T WIRE SPECIFICATIONS**

19-Ga wire; 1-Twin wrap/tie; 215-ft/spool; RB441T - 145-265 ties/spool\* RB61TT - 170-205\* \*based on rebar size







**TW1061T TW1061T-USA** 

**TW1061T-EG** 

**TW1061T-PC** 

30 spools/box.

	Material	Ingredient	Wire Dia.	Heat Treatment	Tensile Strength	Surface
TW1061T Black Annealed	Low Carbon Steel Wire Rods SAE J403 MAY 94	Carbon 0.13 - 0.18% Mangan 0.60 - 0.90% Phosphorus less than 0.03% Sulfur less than 0.035%	0.0394" 19-Ga	Annealed	55,800-81,300 (lb/in²)	
TW1061T-EG Electro- Galvanized	Low Carbon Steel Wire Rods SAE J403 MAY 94	Carbon 0.13 - 0.18% Mangan 0.60 - 0.90% Phosphorus less than 0.03% Sulfur less than 0.035%	0.0394" 19-Ga	Annealed	55,800-81,300 (lb/in²)	Electric Galv. 1 µm or more
TW1061T-PC Plastic Coated	Low Carbon Steel Wire Rods SAE J403 MAY 94	Carbon 0.13 - 0.18% Mangan 0.60 - 0.90% Phosphorus less than 0.03% Sulfur less than 0.035%	0.0394" 19-Ga (Without Surface Treatment)	Annealed	55,800-81,300 (lb/in²)	Polyester Coated 0.00197" (0.65mm)

## STRENGTH COMPARISON BETWEEN MAX TW1061T WIRE AND REGULAR 16-GAUGE TIE

	Diameter	Area / Wraps (a)	Wraps / Tie (b)	Area / Tie (a x b)
TW1061T (19-Gauge)	.0394"	.00122 in <sup>2</sup>	1-Twin	.00243 in <sup>2</sup>
16-Gauge Tie Wire	.0551"*	.00238 in²	1	.00238 in <sup>2</sup>

\*This number was measured from sample 16-gauge wire in the market.

The strength of tie wire is in proportion to the sum of area of wire wrapping rebars, therfore, the strength of 1-Twin wrap by MAX TW1061T is equivalent to regular 16-gauge wire.



USA Made, BUY AMERICA Certified Wire, and can be used in the RB218, RB398, RB441T, RB611T, and the RB518 rebar tiers.







# **TW898 WIRE SPECIFICATIONS**

21-Ga wire; 3 wraps/tie; 312-ft/spool; Up to 120 ties/spool (based on rebar size); 50 spools/box.



TW898 TW898-USA



TW898-EG



TW898-PC

	Material	Ingredient	Wire Dia.	Heat Treatment	Tensile Strength	Surface
TW898 Black Annealed	Low Carbon Steel Wire Rods SAE J403MAY94	Carbon 0.13 - 0.18% Mangan 0.60 - 0.90% Phosphorus less than 0.03% Sulfur less than 0.035%	0.0315" 21-Ga	Annealed	68.226 - 81.290 (lb/in²)	
TW898-EG Electro- Galvanized	Low Carbon Steel Wire Rods SAE J403MAY94	Carbon 0.13 - 0.18% Mangan 0.60 - 0.90% Phosphorus less than 0.03% Sulfur less than 0.035%	0.0315" 21-Ga	Annealed	68.226 - 81.290 (lb/in²)	Electric Galv. 1 µm and over Production Avg 4.29 µm
TW898-PC Plastic Coated	Low Carbon Steel Wire Rods SAE 1016L	Carbon 0.13 - 0.18% Mangan 0.60 - 0.90% Phosphorus less than 0.03% Sulfur less than 0.035%	0.0315" 21-Ga	Annealed	55.887 - 81.290 (lb/in²)	Plastic Coated 0.00197" (0.05mm)

## STRENGTH COMPARISON BETWEEN MAX TW898 WIRE AND REGULAR 16-GAUGE TIE WIRE

	Diameter	Area / Wraps (a)	Wraps / Tie (b)	Area / Tie (a x b)
TW898 (21-Gauge)	.0315"	.00078 in <sup>2</sup>	3	.00234 in²
16-Gauge Tie Wire	.0551"*	.00238 in²	1	.00238 in <sup>2</sup>

\*This number was measured from sample 16-gauge wire in the market.

The strength of tie wire is in proportion to the sum of area of wire wrapping rebars, therfore, the strength of three wraps by MAX TW898 is equivalent to regular 16-gauge wire.



*USA Made*, *BUY AMERICA Certified Wire*, and can be used in the RB218, RB398, RB441T, RB611T, and the RB518 rebar tiers.







## TIE WIRE SPECIFICATIONS & SAFETY DATA

**TW1525 WIRE SPECIFICATIONS** 

16-Ga wire;1 wrap/tie;82-ft/spool;120-230 ties/spool (based on rebar size);50 spools/box.



**TW1525** 



TW1525-EG



TW1525-PC

	Material	Ingredient	Wire Dia.	Heat Treatment	Tensile Strength	Surface
<b>TW1525</b> Black Annealed	Low Carbon Steel Wire Rods	Carbon less than 0.08% Mangan less than 0.60% Phosphorus less than 0.045% Sulfur less than 0.045%	0.059" 16-Ga	Annealed	41,336 - 52,939 (lb/in²)	
TW1525-EG Electro- Galvanized	Low Carbon Steel Wire Rods	Carbon less than 0.08% Mangan less than 0.60% Phosphorus less than 0.045% Sulfur less than 0.045%	0.059" 16-Ga	Annealed	41,336 - 52,939 (lb/in²)	Electric Galv. 1 µm and over Production Avg 3.54 µm
TW1525-PC Plastic Coated	Low Carbon Steel Wire Rods	Carbon less than 0.08% Mangan less than 0.60% Phosphorus less than 0.045% Sulfur less than 0.045%	0.059" 16-Ga	Annealed	41,336 - 52,939 (lb/in²)	Plastic Coated 0.00197" (0.05mm)

